

# COX STUD WELDING

## CD STUD STANDARD LOAD CAPACITIES

STUD MATERIAL	STUD SIZE	MAX FASTENING TORQUE (INCH/LBS)	ULTIMATE TENSILE LOAD (LBS)	MAX SHEAR LOAD (LBS)
<b>LOW-CARBON COPPER FLASHED STEEL</b>	6-32	6.0	500	375
	8-32	12.0	765	575
	10-24	14.0	960	720
	1/4-20	43.0	1,750	1,300
	5/16-18	72.0	2,900	2,200
	3/8-16	106.0	4,300	3,250
<b>STAINLESS STEEL: 304</b>	6-32	10.0	790	590
	8-32	20.0	1,260	940
	10-24	23.0	1,530	1,150
	1/4-20	43.0	2,880	2,160
	5/16-18	72.0	2,900	5,350
	3/8-16	106.0	4,300	7,150
<b>ALUMINUM ALLOY: 1100</b>	6-32	2.5	200	125
	8-32	5.0	295	185
	10-24	6.5	380	235
	1/4-20	21.5	670	415
	5/16-18	36.0	1,125	695
	3/8-16	53.0	1,660	1,000
<b>ALUMINUM ALLOY: 5068</b>	6-32	3.5	375	235
	8-32	7.5	585	365
	10-24	10.0	735	460
	1/4-20	32.5	1,360	850
	5/16-18	54.5	2,300	1,400
	3/8-16	81.0	3,400	2,100
<b>BRASS: 70-30/65-35</b>	6-32	8.0	600	390
	8-32	16.0	860	560
	10-24	18.5	1,040	680
	1/4-20	61.0	1,950	1,275
	5/16-18	102.0	3,280	2,140
	3/8-16	150.0	4,800	3,160

MAXIMUM FASTENING TORQUE SHOULD DEVELOP FASTENER TENSION TO SLIGHTLY LESS THAN YIELD POINT.